

Specifications for NuShield Standard Antiglare (AG) film

Property	Value	Test Method
Burst Strength	1.75 MPa	ASTM D774-67
Elastic Modulus	4-5.5 GPa	ASTM D882-83 23° C, 50% RH. Strain Rate-10% per minute
Gardner Haze	5-7% - Antiglare	ASTM D1003-77
Gloss Level @ 60°	85±5% - Antiglare	ASTM D2457-70
Total Luminous Transmission	>90%	ASTM D1003-77
Clarity	>75%	BYK-Gardner
Dimensional Stability	0.2% max shrinkage	MD @ 120° C
Pencil Hardness	3-4H @ 45°	ASTM D3363
Chemical resistance	Resistant to: Alcohols Dilute acids Dilute alkalis Esters Hydrocarbons Ketones Household cleaning agents	DIN 42 115